



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd  
NO.205 Jiangtian RD(E).,Songjiang  
Shanghai China  
Postal Code: 201613  
Tel:(021)57747878  
Fax:(021)51685279  
Website: <https://www.escort.com.cn/CN>

## TEST REPORT

MATERIAL : FKM 60 DURO BLACK

COMPOUND NO: V6001B

| Physical Properties (Press Cure:170°CX10min Post Cure:230°CX24h) | Requirement | Test result |
|------------------------------------------------------------------|-------------|-------------|
| Hardness,Point 硬度(邵A)                                            | 55.00~65.00 | 62.00       |
| Tensile Strength,min,Mpa 拉力強度                                    | 7.00        | 8.00        |
| Ultimate Elongation,min,% 延伸率                                    | 200.00      | 222.00      |
| Specific Gravity, 比重                                             |             | 1.81        |
| Heat Resistance 70h@250°C 老化試驗                                   |             |             |
| Change in hardness,max,Point 硬度變化(邵A)                            | +10.00      | +0.00       |
| Change in tensile strength,max,% 拉伸強度變化率                         | -25.00      | +0.00       |
| Change in ultimate elongation,max,% 扯斷伸長率變化率                     | -25.00      | -2.00       |
| Compression Set 22h@175°C 壓縮永久變形試驗                               |             |             |
| Compression set,Method B,max,% 壓縮永久變形                            | 50.00       | 4.00        |

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
THIS COMPOUND V6001B CAN MEET ASTM 2000 M2HK607A1-10B37

