

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : NBR 60 DURO RED

COMPOUND NO: N6001R

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness, Point 硬度(邵A)	55.00-65.00	65.00
Tensile Strength, min, Mpa 拉力強度	6.00	10.00
Ultimate Elongation, min, % 延伸率	200.00	630.00
Specific Gravity, 比重		1.41
Heat Resistance 70h@100°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	±15.00	+5.00
Change in tensile strength, max, % 拉伸強度變化率	±30.00	+8.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-50.00	-1.00
Compression Set 22h@100°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	25.00	21.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND N6001R CAN MEET ASTM 2000 M2BG606A14B14

