



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: <https://www.escort.com.cn/CN>

TEST REPORT

MATERIAL : AFLAS 70 DURO BLACK

COMPOUND NO: L7001B

Physical Properties (Press Cure:170°CX10min Post Cure:200°CX16h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	75.00
Tensile Strength,min,Mpa 拉力強度	14.00	19.50
Ultimate Elongation,min,% 延伸率	175.00	238.00
Specific Gravity, 比重		1.57
Heat Resistance 70h@250°C 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+10.00	-3.00
Change in tensile strength,max,% 拉伸強度變化率	-25.00	-15.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-25.00	+20.00
Compression Set 22h@200°C 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	50.00	28.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND L7001B CAN MEET ASTM 2000 M2HK714A1-10B38

